

**TECHNICAL FEATURES**

Collection: Realstone_argent ptv Surface: Natural	Brand: Ragno
Size (cm): 60x120 RT - 60x60 RT - 30x60 RT	Thickness (mm): 9,5

Compliant with standard EN 14411:2016 annex G group BIa - UGL

Compliant with standard ISO 13006:2018 annex G group BIa - UGL

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits		
<b>DIMENSIONAL PROPERTIES AND SURFACE QUALITY</b>						
Dimensions				Nominal Length of edge N (cm) 7≤N<15 Nominal Length of edge N (cm) N≥15		
<b>Length and width (*)</b>	ISO 10545-2	(mm) (%)	Complies with the standards	±2% (max 5mm)	±2% (max 5mm) ±2% (max 5mm)	
<b>Length and width (**)</b>						
Not Rectified						
Rectified					Complies with the standards	±0,9 mm ±0,6% ±2,0 mm ±0,4 mm ±0,3% ±1,0 mm
<b>Thickness</b>						
Not Rectified						
Rectified					Complies with the standards	±0,5 mm ±5% ±0,5 mm ±0,5 mm ±5% ±0,5 mm
<b>Straightness of sides</b>						
Not Rectified						
Rectified					Complies with the standards	±0,75 mm ±0,5% ±1,5 mm ±0,4 mm ±0,3% ±0,8 mm
<b>Rectangularity</b>						
Not Rectified						
Rectified					Complies with the standards	±0,75 mm ±0,5% ±2,0 mm ±0,4 mm ±0,3% ±1,5 mm
<b>Surface Flatness c.c - e.c. - w.</b>						
Not Rectified						
Rectified					Complies with the standards	±0,75 mm ±0,5% ±2,0 mm ±0,6 mm ±0,4% ±1,8 mm
<b>Surface Quality</b>					Complies with the standards	≥95%
<b>PHYSICAL PROPERTIES</b>						
Water absorption	ISO 10545-3	(%)	≤ 0,5	Eb ≤ 0,5 (Individual maximum value 0,6%)		
Modulus of rupture	ISO 10545-4	(N/mm <sup>2</sup> )	≥35	R ≥35 (Individual minimum value 32 N/mm <sup>2</sup> )		
Breaking Strength	ISO 10545-4	(N)	≥1300	≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm)		
Resistance to deep abrasion	ISO 10545-6	(mm <sup>3</sup> )	<175	≤175		
Resistance to surface abrasion	Internal Method		Intended use - Class H			
Linear thermal expansion coefficient	ISO 10545-8	(x(10)-6/°C)	≤ 9	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)		
Thermal shock resistance	ISO 10545-9		Complies with the standards	Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018)		
Frost resistance	ISO 10545-12		Complies with the standards	Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018)		
Reaction to fire	-	-	Floor/Wall Class A1 FL / A1	Class A1 or Class A1 FL		
Colour resistance to light exposure	DIN 51094		Complies with the standards	No sample must show noticeable colour modifications.		

**TECHNICAL FEATURES**

Collection: Realstone_argent ptv Surface: Natural	Brand: Ragno
Size (cm): 60x120 RT - 60x60 RT - 30x60 RT	Thickness (mm): 9,5

Technical Features	Testing Method	Meas. unit	Average Typical Values	Established limits
<b>CHEMICAL PROPERTIES</b>				
Resistance to chemicals for household use and swimming pool salts	ISO 10545-13		A	UB Minimum (EN 14411:2016) UB Minimum (ISO 13006:2018)
Resistance to low concentrations of acids and alkalis	ISO 10545-13		LA-LB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Resistance to high concentrations of acids and alkalis	ISO 10545-13		HA-HB	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
Stain resistance	ISO 10545-14		Class 5	Declared value (EN 14411:2016) Test Method available (ISO 13006:2018)
<b>ANTISLIIPPY PROPERTIES</b>				
Slipperiness Resistance: Ramp Method	DIN 51130 DGUV Regel 108-003		R10	from R9 to R13
Slipperiness Resistance: Ramp Method	DIN 51097 DGUV Information 207-006		B(A+B)	from A to C
Slipperiness Resistance: B.C.R.	D.M. N.236 14/6/89		$\mu > 0,40$	$\mu > 0,40$
Slipperiness Resistance: Pendulum	UNE 41901:2017 EX DB SUA (actual)		Class 2	from Class 0 to Class 3
Slipperiness Resistance: Pendulum	BS7976-2:2002 / BSEN13036-4:2011		>36	0 - 24 Slippery; 25 - 35 Moderately slippery; 36+ Low slipping risk
Dynamic coefficient of friction (DCOF)	ANSI A326.3:2017		>0,42	$\geq 0,42$

\* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

\*\* The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

\*\*\*\* See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.